

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (Currently Amended) A stator for a dynamo-electric machine comprising:  
a stator core having a plurality of slots; and  
a stator winding installed in said slots, said stator winding comprising a plurality of conductors including end portions joined to each other by a metal to form joint portions, wherein said metal is interposed between said end portions of said conductors ~~without covering outer end surfaces and edges of said end portions~~ and has a melting point which is lower than a melting point of said conductors.
2. (Previously Presented) A stator for a dynamo-electric machine according to claim 1, wherein said metal comprises an alloy of a material of said conductors and an additive metal.
3. (Previously Presented) A stator for a dynamo-electric machine according to claim 2, wherein said additive metal is a Cu--P alloy.
4. (Previously Presented) A stator for a dynamo-electric machine according to claim 2, wherein said additive metal comprises Ag or an Ag alloy.

AMENDMENT UNDER 37 C.F.R. § 1.116  
U.S. Patent Application No. 09/888,656

5. (Previously Presented) A stator for a dynamo-electric machine according to claim 2, wherein said additive metal comprises Sn or an Sn alloy.

6. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine comprising,

in a stator comprising a stator core having a plurality of slots, and a stator winding installed in said slots and comprising a plurality of conductors joint end portions thereof joined to each other,

an insert metal positioning process for placing an insert metal of a lower melting point than that of said conductors between said joint end portions of said conductors, and

after heating a vicinity of said joint end portions to a temperature at which said insert metal melts and said joint end portions do not melt and said insert metal is melted, a joining process for solidifying said insert metal and joining said joint end portions by ending said heating.

7. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine comprising,

in a stator comprising a stator core having a plurality of slots, and a stator winding installed in said slots and comprising a plurality of conductors joint end portions thereof joined to each other,

AMENDMENT UNDER 37 C.F.R. § 1.116  
U.S. Patent Application No. 09/888,656

an insert metal positioning process for placing an insert metal of a lower melting point than that of said conductors between said joint end portions of said conductors, and after heating a vicinity of said joint end portions to a temperature at which said insert metal melts and melt alloying conductor end portions and said insert metal, a joining process for solidifying said molten alloy and joining said joint end portions by ending said heating.

8. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine according to claim 6 wherein:

pairs of said joint end portions to be joined align in a row of two (2) or more sets in a radial direction, and said insert metal is not provided between adjacent sets of said joint end portions.

9. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine according to claim 6 wherein:

pairs of said joint end portions to be joined align in a row of a plurality of sets in a circumferential direction, and said insert metal provided between each said joint end portion is connected in a circumferential direction.

10. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine according to claim 9 wherein:

AMENDMENT UNDER 37 C.F.R. § 1.116  
U.S. Patent Application No. 09/888,656

a cross sectional area of a connecting portion of said insert metal is smaller than a cross sectional area of a portion between said joint end portions.

11. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine according to claim 6 wherein:

    said vicinity of said joint end portions is heated with a non-contact heat source in said joining process.

12. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine according to claim 9 wherein:

    said joining process is resistance heating in which an electrode is contacted to said joint end portions and a current is conducted, two (2) or more sets of said joint end portions aligned in a radial direction being sandwiched together by two (2) electrodes disposed at an inner diameter side and an outer diameter side and heated.

13. (Withdrawn) A method for manufacturing a stator for a dynamo-electric machine according to claim 12 wherein:

    said two (2) electrodes disposed at an inner diameter side and an outer diameter side are each of a roller shape and heat, while rolling, an inner side and outer side of joint end portion groups aligned in a row of a plurality of sets in a circumferential direction.

AMENDMENT UNDER 37 C.F.R. § 1.116  
U.S. Patent Application No. 09/888,656

14. (Previously Presented) A stator for a dynamo-electric machine according to claim 1, wherein said joint portions have a continuous planar surface where said end portions are joined by said metal.

15. (New) A stator for a dynamo-electric machine according to claim 1, wherein said metal is interposed between said end portions of said conductors without covering outer end surfaces and edges of said end portions.